

# TECHNICAL DATA SHEET



## PHENOL CELLOBOND J2027 X

---

### DESCRIPTION

Cellobond J2027 X is an unmodified liquid phenolic resole resin.

### TYPICAL PROPERTIES

Property	Value
Viscosity at 25 °C	150 - 220 cS
Specific gravity at 25 °C	1.220 - 1.230 g/ml
Free Formaldehyde	1.0% max
pH	7.0 - 7.6
Water content	14.0 - 16.0%
Pot Life	5 - 8 mins
Storage life	3 months

### HEALTH AND SAFETY

Please read the relevant Material Safety Data Sheet CAREFULLY.  
This material should be stored and handled in accordance with good industrial hygiene and safety practices.

06/2016

All information is given, based upon our best knowledge, but without liability to us. Data has been obtained by laboratory experiments made by our supplier. Since the condition under which the product is consumed is outside of our control, the product should be tested before use.